

**Listing of Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1-32. (Cancelled)

33. (New) A nonwoven composite, comprising:

a non-woven material;

a film layer adhered to said non-woven material, said film layer prepared from a blended composition comprising

a) an unsaturated block copolymer, and

b) a compatibilizer including a styrenic block copolymer, wherein said compatibilizer has a melt flow rate of about 20 g/10 min. or more.

34. (New) The composite of claim 33, wherein said compatibilizer contains styrene-butadiene-styrene, styrene-isopropene-styrene, or combinations thereof.

35. (New) The composite of claim 33, wherein said unsaturated block copolymer is a styrene-isoprene-styrene block copolymer.

36. (New) The composite of claim 33, wherein said unsaturated block copolymer is a styrene-butadiene-styrene block copolymer.

37. (New) The composite of claim 33, wherein said compatibilizer has a melt flow rate of about 30 g/10 min. or more.

38. (New) The composite of claim 33, wherein said compatibilizer has a melt flow rate of about 40 g/10 min. or more.

39. (New) The composite of claim 33 wherein said compatibilizer has a melt flow rate of from about 20 g/10 min. to about 50 g/10 min.

40. (New) The composite of claim 33, wherein said unsaturated block copolymer and said compatibilizer are present in a ratio from about 95:5 to about 80:20.

41. (New) The composite of claim 33, wherein said unsaturated block copolymer is a styrene-isoprene-styrene block copolymer and said compatibilizer is a styrene-butadiene-styrene block copolymer.

42. (New) The composite of claim 41, wherein said styrene-isoprene-styrene and styrene-butadiene-styrene are present in said blended composition in a ratio of about 2:1.

43. (New) The composite of claim 33, wherein said compatibilizer has a styrene content by weight of at least about ten percent.

44. (New) The composite of claim 33, wherein said compatibilizer has a styrene content by weight of at least about twenty percent.

45. (New) The composite of claim 33, wherein said compatibilizer has a styrene content by weight of at least about thirty percent.

46. (New) The composite of claim 33, wherein said compatibilizer has a styrene content by weight of at least forty percent.

47. (New) The composite of claim 33, wherein said nonwoven material comprises a necked, spunbond material.

48. (New) The composite of claim 33, wherein said nonwoven material comprises a corrugated, spunbond material.

49. (New) The composite of claim 33, wherein said nonwoven material comprises a meltblown material.

50. (New) The composite of claim 33, wherein said composite has a first cycle hysteresis value of less than about 70 percent.